

Test	Unit	Specifications	Test Result	Test Method
MgO	wt/wt %	96.0 min	97.54	By Difference
CaO	wt/wt %	2.0 max	1.75	DIN 51001
Al ₂ O ₃	wt/wt %	0.2 max	0.05	DIN 51001
SiO ₂	wt/wt %	1.5 max	0.60	DIN 51001
Fe ₂ O ₃	wt/wt %	0.05 max	0.05	DIN 51001
Particle Size (%-45 μm)	% wt/wt	95 min	99	DIN EN 725-5

*All metal oxide results are reported on Loss Free Basis